



Masterbatches e Additivi per Materie Plastiche ed Elastomeri

**FERRO-PLAST S.r.l.**

Via Grandi, 25 - 20090 Vimodrone (Mi)

Tel. +39.02.27409415 Fax +39.02.27409420 E-mail [ferroplast@ferroplast.com](mailto:ferroplast@ferroplast.com) [www.ferroplast.com](http://www.ferroplast.com)

**FerroStab PP UV 66-20**

Informazioni Tecniche

## UV STABILIZER MASTERBATCH

### Typical Properties:

Active Ingredients:	10% HALS II + 10% HALS III
Normal Addition Level:	1.0% to 1.5%
Food Contact	3%
Type:	UV stabilizer Masterbatch
Carrier Resin:	Homopolymer PP MFI 25g/10 mins. 2.16 kg./230°C
Colour:	Natural
Storage:	Six months if stored in dry conditions away from direct sunlight

### Applications

Synergism is obtained when mixtures of the two high-molecular weight HALS are used in PP fibers. These mixtures offer superior UV light resistance, good long-term heat stability and economic costs.

The diagram below illustrates the performance of these materials in PP fibers.

#### XENOTEST 1200 (BPT 53°C) EXPOSURE kLy to 50% retained tensile strength

